

Amkor Technologies Flip-Chip Package Assembly

Qualification Report

RPT084 (v1.0) August 24, 2007





Xilinx is disclosing this Document and Intellectual Property (hereinafter “the Design”) to you for use in the development of designs to operate on, or interface with Xilinx FPGAs. Except as stated herein, none of the Design may be copied, reproduced, distributed, republished, downloaded, displayed, posted, or transmitted in any form or by any means including, but not limited to, electronic, mechanical, photocopying, recording, or otherwise, without the prior written consent of Xilinx. Any unauthorized use of the Design may violate copyright laws, trademark laws, the laws of privacy and publicity, and communications regulations and statutes.

Xilinx does not assume any liability arising out of the application or use of the Design; nor does Xilinx convey any license under its patents, copyrights, or any rights of others. You are responsible for obtaining any rights you may require for your use or implementation of the Design. Xilinx reserves the right to make changes, at any time, to the Design as deemed desirable in the sole discretion of Xilinx. Xilinx assumes no obligation to correct any errors contained herein or to advise you of any correction if such be made. Xilinx will not assume any liability for the accuracy or correctness of any engineering or technical support or assistance provided to you in connection with the Design.

THE DESIGN IS PROVIDED “AS IS” WITH ALL FAULTS, AND THE ENTIRE RISK AS TO ITS FUNCTION AND IMPLEMENTATION IS WITH YOU. YOU ACKNOWLEDGE AND AGREE THAT YOU HAVE NOT RELIED ON ANY ORAL OR WRITTEN INFORMATION OR ADVICE, WHETHER GIVEN BY XILINX, OR ITS AGENTS OR EMPLOYEES. XILINX MAKES NO OTHER WARRANTIES, WHETHER EXPRESS, IMPLIED, OR STATUTORY, REGARDING THE DESIGN, INCLUDING ANY WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, TITLE, AND NONINFRINGEMENT OF THIRD-PARTY RIGHTS.

IN NO EVENT WILL XILINX BE LIABLE FOR ANY CONSEQUENTIAL, INDIRECT, EXEMPLARY, SPECIAL, OR INCIDENTAL DAMAGES, INCLUDING ANY LOST DATA AND LOST PROFITS, ARISING FROM OR RELATING TO YOUR USE OF THE DESIGN, EVEN IF YOU HAVE BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES. THE TOTAL CUMULATIVE LIABILITY OF XILINX IN CONNECTION WITH YOUR USE OF THE DESIGN, WHETHER IN CONTRACT OR TORT OR OTHERWISE, WILL IN NO EVENT EXCEED THE AMOUNT OF FEES PAID BY YOU TO XILINX HEREUNDER FOR USE OF THE DESIGN. YOU ACKNOWLEDGE THAT THE FEES, IF ANY, REFLECT THE ALLOCATION OF RISK SET FORTH IN THIS AGREEMENT AND THAT XILINX WOULD NOT MAKE AVAILABLE THE DESIGN TO YOU WITHOUT THESE LIMITATIONS OF LIABILITY.

CRITICAL APPLICATIONS DISCLAIMER: XILINX PRODUCTS (INCLUDING HARDWARE, SOFTWARE AND/OR IP CORES) ARE NOT DESIGNED OR INTENDED TO BE FAIL-SAFE, OR FOR USE IN ANY APPLICATION REQUIRING FAIL-SAFE PERFORMANCE, SUCH AS LIFE-SUPPORT OR SAFETY DEVICES OR SYSTEMS, CLASS III MEDICAL DEVICES, NUCLEAR FACILITIES, APPLICATIONS RELATED TO THE DEPLOYMENT OF AIRBAGS, OR ANY OTHER APPLICATIONS THAT COULD LEAD TO DEATH, PERSONAL INJURY OR SEVERE PROPERTY OR ENVIRONMENTAL DAMAGE (INDIVIDUALLY AND COLLECTIVELY, “CRITICAL APPLICATIONS”). FURTHERMORE, XILINX PRODUCTS ARE NOT DESIGNED OR INTENDED FOR USE IN ANY APPLICATIONS THAT AFFECT CONTROL OF A VEHICLE OR AIRCRAFT, UNLESS THERE IS A FAIL-SAFE REDUNDANCY FEATURE (WHICH DOES NOT INCLUDE USE OF SOFTWARE TO IMPLEMENT THE REDUNDANCY) AND A WARNING SIGNAL UPON FAILURE TO THE OPERATOR. CUSTOMER AGREES, PRIOR TO USING OR DISTRIBUTING ANY SYSTEMS THAT INCORPORATE XILINX PRODUCTS, TO THOROUGHLY TEST THE SAME FOR SAFETY PURPOSES. CUSTOMER ASSUMES THE SOLE RISK AND LIABILITY OF ANY USE OF XILINX PRODUCTS IN CRITICAL APPLICATIONS, SUBJECT ONLY TO APPLICABLE LAWS AND REGULATIONS GOVERNING LIMITATIONS ON PRODUCT LIABILITY.

© 2007 Xilinx, Inc. All rights reserved. XILINX, the Xilinx logo, and other designated brands included herein are trademarks of Xilinx, Inc. All other trademarks are the property of their respective owners.

Revision History

The following table shows the revision history for this document.

Date	Version	Revision
08/24/07	1.0	Initial Xilinx release.

Table of Contents

Overview 5
Qualification Objective 5
Qualification Matrix 6
Reliability Test Conditions and Results 7

Amkor Technologies Flip-Chip Package Assembly Qualification

Overview

This report summarizes the Reliability Test results collected to date that were performed to qualify Amkor Technologies as an assembly site for Flip-Chip packaged devices.

All qualification lots completed reliability stress tests, except one Temperature Humidity Biased (THB) lot that completed 500 hours and passed at the post-electrical test. The THB lot is being continued to 1000 hours. When the 1000-hour data become available, this report will be updated with these additional data.

Qualification Objective

The objective of this qualification is to qualify Amkor Technologies as an assembly site for manufacturing the Flip-Chip packaged devices.

Qualification Matrix

Table 1: Qualification Matrix

Package Size	27 mm			31 mm	35 mm		40 mm	
Pin count	FF(G)672	FF(G)668	FF(G)676	FF(G)896	FF(G)1148	FF(G) 1152	FF(G)1513	FF(G)1517
XC2VP2	A							
XC2VP4	A							
XC2VP7	A			A				
XC2VP20				A		A		
XC2VP30				A		A		
XC2VP40					A	A		
XC2VP50					A	A (TV)		A
XC4VSX25		B						
XC4VSX35		B						
XC4VSX55					C			
XC4VFX12		B						
XC4VFX20	B							
XC4VFX40	B					C		
XC4VFX60	B					C		
XC4VFX100						C		D
XC4VFX140								D
XC4VLX15		B	B					
XC4VLX25		B	B					
XC4VLX40		B			C			
XC4VLX60		B (TV)			C			
XC4VLX80					C			
XC4VLX100					C (TV)		D	
XC4VLX160					D		D	
XC4VLX200							D (TV)	

In Table 1, the test vehicles marked with X (TV), where X = A, B, C, or D, were selected based on their similarity and die size. The packaged devices marked with A, B, C, and D are qualified by extension of A (TV), B (TV), C (TV), and D (TV) respectively.

Reliability Test Conditions and Results

The qualification vehicles were selected from several different product families as well as several different package sizes and pin counts for reliability tests. [Table 2](#) provides a summary of the qualification.

Table 2: Qualification Summary

Test	Conditions	Test Vehicle	Lot Qty	Cum Device-Hr/Cyc	# of Failures
TC-B ⁽¹⁾	-55 to +125°C	XC2VP50/FFG1152	2	145,000	0
		XC4VLX60/FFG668	1	82,000	0
		XC4VLX100/FFG1148	6	144,000	0
		XC4VLX200/FFG1513	1	75,000	0
THB ⁽¹⁾	85°C, 85%RH, V _{DDMAX}	XC4VLX100/FFG1148	6	74,000	0
HTS ⁽²⁾	T _A =150°C	XC4VLX100/FFG1148	6	96,000	0
TH ⁽¹⁾	85°C, 85%RH	XC4VLX100/FFG1148	6	90,000	0

Notes:

1. Level-4 preconditioning applied to THB and TC-B samples prior to the stress tests.
2. Reflow (3X) applied to HTS samples prior to the stress test.

Based on the data gathered thus far, XC2VP50/FFG1152 [A(TV)], XC4VLX60/FFG668 [B(TV)] and XC4VLX200/FFG1513 [D(TV)] have completed all the stress tests and met the requirements for production release. XC4VLX100/FFG1148 will be qualified pending the completion of a 1000-hour THB on 1 lot.

Environmental Stress Data

Table 3: Environmental Stress Data

Test	Conditions	Rel #	Device	Package	Samples	Duration	Fail Qty	
TC-B ⁽¹⁾	-55 to +125°C	208207	XC2VP50	FFG1152	73	1,000 cycles	0	
		208307	XC2VP50	FFG1152	72	1,000 cycles	0	
		203807	XC4VLX60	FFG668	82	1,000 cycles	0	
		234207	XC4VLX200	FFG1513	75	1,000 cycles	0	
		213607	XC4VLX100	FFG1148	24	1,000 cycles	0	
		214007	XC4VLX100	FFG1148	24	1,000 cycles	0	
		214407	XC4VLX100	FFG1148	24	1,000 cycles	0	
		214807	XC4VLX100	FFG1148	24	1,000 cycles	0	
		215207	XC4VLX100	FFG1148	24	1,000 cycles	0	
		215607	XC4VLX100	FFG1148	24	1,000 cycles	0	
THB ⁽¹⁾	85°C, 85%RH, V _{DDMAX}	213807	XC4VLX100	FFG1148	14	500 hrs ⁽³⁾	0	
		214207	XC4VLX100	FFG1148	14	1,000 hrs.	0	
		214607	XC4VLX100	FFG1148	13	1,000 hrs.	0	
		215007	XC4VLX100	FFG1148	14	1,000 hrs.	0	
		215407	XC4VLX100	FFG1148	13	1,000 hrs.	0	
		215807	XC4VLX100	FFG1148	13	1,000 hrs.	0	

Table 3: Environmental Stress Data (Continued)

Test	Conditions	Rel #	Device	Package	Samples	Duration	Fail Qty	
HTS ⁽²⁾	T _A = 150°C	213707	XC4VLX100	FFG1148	16	1,000 hrs.	0	
		214107	XC4VLX100	FFG1148	16	1,000 hrs	0	
		214507	XC4VLX100	FFG1148	16	1,000 hrs	0	
		214907	XC4VLX100	FFG1148	16	1,000 hrs	0	
		215307	XC4VLX100	FFG1148	16	1,000 hrs	0	
		215707	XC4VLX100	FFG1148	16	1,000 hrs	0	
TH ⁽¹⁾	85°C, 85%RH, No bias	213907	XC4VLX100	FFG1148	15	1,000 hrs.	0	
		175807	XC4VLX100	FFG1148	15	1,000 hrs.	0	
		174707	XC4VLX100	FFG1148	15	1,000 hrs	0	
		215107	XC4VLX100	FFG1148	15	1,000 hrs	0	
		215507	XC4VLX100	FFG1148	15	1,000 hrs	0	
		215907	XC4VLX100	FFG1148	15	1,000 hrs	0	

Notes:

1. Level-4 preconditioning applied to THB and TC-B samples prior to the stress tests.
2. Reflow (3X) applied to HTS samples prior to the stress test.
3. The THB lot is being continued to 1,000 hours.

