



100% Material Declaration Data Sheet for UltraScale FFVC1517

PK768 (v1.0) October 2, 2015

Average Weight: 15.270g

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Silicon Die					0.731163	4.788%
	Silicon (Si)	7440-21-3	100.00	Basis	0.731163	
Solder Bump					0.028328	0.186%
	Tin (Sn)	7440-31-5	98.20	Basis	0.027818	
	Silver (Ag)	7440-22-4	1.80	Basis	0.000510	
Solder Paste					0.013440	0.088%
	Tin (Sn)	7440-31-5	96.50	Metal	0.012970	
	Silver (Ag)	7440-22-4	3.00	Metal	0.000403	
	Copper (Cu)	7440-50-8	0.50	Metal	0.000067	
Capacitor 1					0.033600	0.220%
	Barium oxide	1304-28-5	30.22	Ceramic	0.010154	
	Titanium dioxide	13463-67-7	15.11	Ceramic	0.005077	
	Misc.	trade secret	5.04	Ceramic	0.001693	
	Nickel (Ni)	7440-02-0	33.44	Inner electrode	0.011236	
	Copper (Cu)	7440-50-8	11.87	Outer electrode	0.003988	
	Silicon dioxide	7631-86-9	1.06	Outer electrode	0.000356	
	Boric oxide	1303-86-2	0.26	Outer electrode	0.000087	
	Nickel (Ni)	7440-02-0	0.81	Nickel Plating Layer	0.000272	
	Tin (Sn)	7440-31-5	2.19	Tin Plating Layer	0.000736	
Capacitor 2					0.019320	0.127%
	Barium oxide	1304-28-5	31.67	Ceramic	0.006119	
	Titanium dioxide	13463-67-7	15.83	Ceramic	0.003058	
	Misc.	trade secret	5.28	Ceramic	0.001020	
	Nickel (Ni)	7440-02-0	26.67	Inner electrode	0.005153	
	Copper (Cu)	7440-50-8	15.10	Outer electrode	0.002917	
	Silicon dioxide	7631-86-9	1.34	Outer electrode	0.000259	
	Boric oxide	1303-86-2	0.33	Outer electrode	0.000064	
	Nickel (Ni)	7440-02-0	1.00	Nickel Plating Layer	0.000193	
	Tin (Sn)	7440-31-5	2.78	Tin Plating Layer	0.000537	

© Copyright 2015 Xilinx, Inc. XILINX, the Xilinx logo, Virtex, Spartan, ISE, and other designated brands included herein are trademarks of Xilinx in the United States and other countries. All other trademarks are the property of their respective owners

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Underfill					0.105000	0.688%
	Bisphenol F type liquid epoxy resin	9003-36-5	15.00	Basis	0.015750	
	1,6-Bis(2,3-epoxypropoxy)naphthalene	27610-48-6	10.00	Basis	0.010500	
	Bisphenol A type liquid epoxy resin	25068-38-6	5.00	Basis	0.005250	
	Amine type hardener	trade secret	10.00	Basis	0.010500	
	Silicon dioxide	60676-86-0	58.00	Filler	0.060900	
	Carbon black	1333-86-4	1.00	Color agent	0.001050	
	Additives	trade secret	1.00	Additives	0.001050	
Lid					6.410000	41.978%
	Copper (Cu)	7440-50-8	98.35	Main Material	6.304235	
	Nickel (Ni)	7440-02-0	1.65	Main Material	0.105765	
Lid Adhesive					0.300000	1.965%
	Aluminium Oxide Al ₂ O ₃	1344-28-1	80.00	Main Material	0.240000	
	Dimethyl siloxane, dimethylvinyl-terminated	68083-19-2	20.00	Main Material	0.060000	
Solder Ball					1.267250	8.299%
	Tin (Sn)	7440-31-5	96.50	Main Material	1.222896	
	Silver (Ag)	7440-22-4	3.00	Main Material	0.038018	
	Copper (Cu)	7440-50-8	0.50	Main Material	0.006336	
Substrate					6.361899	41.663%
	Copper (Cu)	7440-50-8	40.49		2.575933	
	Tin (Sn)	7440-31-5	0.64		0.040716	
	Lead (Pb)	7439-92-1	0.00		0.000000	
	Silver (Ag)	7440-22-4	0.02		0.001272	
	BT Core	N/A	43.11		2.742615	
	ABF	N/A	14.24		0.905934	
	Solder Mask	N/A	1.50		0.095428	

Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
10/2/2015	1.0	Initial Xilinx release

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers (“Contractors”). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.