



100% Material Declaration Data Sheet for FFVB2104

PK786 (v1.0) Apr 1, 2016

Average Weight : 32.5513 g

Component	Substance Description	CAS # or Description	% of component	Use in product	Component weight / substance weight (in grams)	Component % of total
Silicon die	Si	7440-21-3	100.00	basis	0.731163	2.246%
					0.731163	
Bump	Sn	7440-31-5	98.20	basis	0.028328	0.087%
	Ag	7440-22-4	1.80	basis	0.000510	
					0.078000	
Underfill	Bisphenol F type liquid epoxy	9003-36-5	15.00	basis	0.011700	0.240%
	1,6-Bis(2,3-epoxypropoxy)naphthalene	27610-48-6	10.00	basis	0.007800	
	Bisphenol A type liquid epoxy resin	25068-38-6	5.00	basis	0.003900	
	Amine type hardener	trade secret	10.00	basis	0.007800	
	Silicon dioxide	60676-86-0	58.00	filler	0.045240	
	Carbon black	1333-86-4	1.00	color agent	0.000780	
	Additives	trade secret	1.00	additives	0.000780	
Solder paste					0.018432	0.057%
	Sn	7440-31-5	96.50	metal	0.017787	
	Ag	7440-22-4	3.00	metal	0.000553	
	Cu	7440-50-8	0.50	metal	0.000092	
Capacitor 1					0.048000	0.147%
	BaTiO3 type	1304-28-5	30.22	Ceramic	0.014506	
	Titanium dioxide	13463-67-7	15.11		0.007253	
	Misc	-	5.04		0.002419	
	Ni	7440-02-0	33.44	Inner electrode	0.016051	
	Cu	7440-50-8	11.87	Out electrode	0.005698	
	Silicon dioxide	7631-86-9	1.06		0.000509	
	diboron trioxide: boric oxide	1303-86-2	0.26		0.000125	
	Ni	7440-02-0	0.81	Plating1	0.000389	
	Sn	7440-31-5	2.19	Plating2	0.001051	
Capacitor2					0.024840	0.076%
	BaTiO3 type	1304-28-5	31.67	Ceramic	0.007867	
	Titanium dioxide	13463-67-7	15.83		0.003932	
	Misc	-	5.28		0.001312	
	Ni	7440-02-0	26.67	Inner Electrode	0.006625	
	Cu	7440-50-8	15.10	Outer Electrode	0.003751	
	Silicon dioxide	7631-86-9	1.34		0.000333	
	diboron trioxide: boric oxide	1303-86-2	0.33		0.000082	
	Ni	7440-02-0	1.00	Plating1	0.000248	
Sn	7440-31-5	2.78	Plating2	0.000691		
Lid					20.237200	62.170%
	Cu	7440-50-8	98.35	Main material	19.903286	
	Ni	7440-02-0	1.65	Main material	0.333914	
Lid Adhesive					0.255000	0.783%
	Aluminium Oxide Al2O3	-	80.00	Main material	0.204000	
	Dimethyl siloxane, dimethylvinyl-terminated	68083-19-2	20.00	Main material	0.051000	
Solder ball					1.757610	5.400%
	Sn	7440-31-5	96.50	Main material	1.696094	
	Ag	7440-22-4	3.00	Main material	0.052728	
	Cu	7440-50-8	0.50	Main material	0.008788	
Substrate					9.372727	28.794%
	Cu	7440-50-8	39.80		3.730345	
	Sn	7440-31-5	0.65		0.060923	
	Ag	7440-22-4	0.02		0.001875	
	BT Core	N/A	41.88		3.925298	
	ABF	N/A	16.21		1.519319	
	Solder Mask	N/A	1.44		0.134967	

Revision History

Date	Version	Description of Revisions
04/01/2016	1	Initial Xilinx release.

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers ("Contractors"). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.